


Emhart Glass 1380-86 Material Technical Data Sheet

Mix ID:	1380-86			
Mix Name:	Ceramic Bulk Fiber			
Type:	Bulk			
Application:	High-temperature loose fill, expansion joints, furnace walls, base seals, tube seals, and packing around hard refractory furnace burner blocks.			
Typicals:	Porosity:	N/A	Chemistry:	Wt. %
 REFRACTORY PRODUCTS	Maximum Use Temperature:	1760°C	Al₂O₃	45.0
			SiO₂	53.0
	Specific Gravity:	2.65 g/cc	ZrO₂	N/A
			Fe₂O₃	.9
	Temperature Grade:	1260°C	Na₂O-K₂O	N/A
			CaO	N/A
			MgO	N/A
			TiO₂	1.0
			Other	Trace

All data is subject to reasonable deviations and not to be used for specification purposes.