



Emhart Glass 330 - Material Technical Data Sheet

Mix ID:	330			
Mix Name:	Mullac			
Type:	Cast			
Application:	Special shapes and burner blocks. Good corrosion resistance and thermal shock resistance.			
Typicals:	Porosity:	21%	Chemistry:	Wt.%
 REFRACTORY PRODUCTS	Density:	2.3 g/cc	Al₂O₃	65.6
			SiO₂	31.6
	Apparent Specific Gravity:	2.9 g/cc	ZrO₂	N/A
			Fe₂O₃	1.0
	MOR:	2300 psi	NaO	N/A
			CaO	.05
	PCE:	37	MgO	.04
			TiO₂	1.4
	Linear Thermal Expansion:	4.9 x 10⁻⁶ (in/in/°C)	Other	.31

Thermal Expansion 330



All data is subject to reasonable deviations and not to be used for specification purposes.